



Testing. Advising. Assuring.

Test report

No. 2014-2041

issued 24.10.2014

Applicant:

BANCROFT SOFT FURNISHINGS LTD
6 RUSSELL COURT, WOOLGATE
BINGLY, BDIG IPE

Date of order:

22.09.2014

Date of sampling:

no official taking out of the specimen from a
representative of the Exova Warringtonfire, Frankfurt

Date of delivery:

22.09.2014

Date of test:

23.10.2014

Order:

Determination of the ignition time according to EN 1101 (ISO 6940) and of the
vertical flame spread according to DIN EN 13772 with classification to DIN EN 13773.

Description / designation of the test object

Textured 3 Pass FR Blackout Petr designated as REF 7034 Palazzo

Description of the relevant test procedure

DIN EN 1101 (09-2005) I. g. EN ISO 6940 (Version 1995)

DIN EN 13772 (04-2011)

DIN EN 13773 (05-2003)

1. Description of the test material

1.1 Details of the customer:

Textured 3 Pass FR Blackout Petr designated as REF 7034 Palazzo

Piece:	150070.15
Description:	Textured 3 Pass FR Blackout Petr designated as REF 7034 Palazzo
Prod.:	PLAZZO/PETROL
Batch No.:	PO4530
Composition:	100% Polyester

Intended end use of product:	Drapery for hotels
---------------------------------	--------------------

1.2 At the specimen preparation from Exova Warringtonfire, Frankfurt determined values:

One side coated fabric

Colour:	fabric surface: petrol, rear: white coated
---------	--

Thickness:	0, 4 mm (average)
------------	-------------------

Square weight:	329 g/m ² (average)
----------------	--------------------------------

Pretreatment:	Material tested as delivered
---------------	------------------------------

Testing after clima storing 23 °C and 50% humidity

2.1.1 Test sheet according to DIN EN 1101 (09-2005) or. EN ISO 6940 (version 1995) (Determination of the ignition time)

Test room: 21 °C / 40% r. L.F.

Ignition times: 1 - 4 s

Specimen no.		1	2	3	4	5	6	7	8
Test direction	L/Q	L	L	L	L	Q	Q	Q	Q
Kind of ignition	E/S	E	E	E	E	E	E	E	E
Ignition time	[s]	1	2	3	4	1	2	3	4
Total burn time	[s]	1	2	5	7	1	2	4	5
After flame time	[s]	0	0	2	3	0	0	1	1
After glow time	[s]	5	3	5	4	3	3	5	5
After flaming ≥ 5 [s]	yes/no	no	no	no	no	no	no	no	no
Reaching of the upper edge of the specimen	yes/no	no	no	no	no	no	no	no	no
Reaching the side edges	yes/no	no	no	no	no	no	no	no	no
Drop of from sample parts*		-	-	-	-	-	-	-	-
Ignition of the filter paper*		-	-	-	-	-	-	-	-
Ignition	yes/no	no	no	no	no	no	no	no	no

If not the case, - L = length Q = width S = surface E = edge

Remarks: none

EN ISO 6940 (1995) paragraph 8.6

...The ignition has taken place, if either the flame on the sample further on at least 5 seconds after the flame is removed, or remove the sample after the flame blows up to the top edge or edges to the vertical.

2.1.2 Test sheet according to DIN EN 1101 (09-2005) or. EN ISO 6940 (version 1995)

(Determination of the ignition time)

Test room: 21 °C / 40% r. L.F.

Ignition times: 1 - 20 s

Specimen no.		9	10	11	12	13	14	15	16
Test direction	L/Q	L	L	L	L	Q	Q	Q	O
Kind of ignition	E/S	E	E	E	E	E	E	E	E
Ignition time	[s]	5	10	15	20	5	10	15	20
Total burn time	[s]	7	9	8	9	7	7	7	7
After flame time	[s]	2	0	0	0	2	0	0	0
After glow time	[s]	5	5	5	5	5	5	5	5
After flaming ≥ 5 [s]	yes/no	no	no	no	no	no	no	no	no
Reaching of the upper edge of the specimen	yes/no	no	no	no	no	no	no	no	no
Reaching the side edges	yes/no	no	no	no	no	no	no	no	no
Drop of from sample parts*		-	-	-	-	-	-	-	-
Ignition of the filter paper*		-	-	-	-	-	-	-	-
Ignition	yes/no	no	no	no	no	no	no	no	no

If not the case, - L = length Q = width S = surface E =edge

Remarks: none

Determined ignition time: none

EN ISO 6940 (1995) paragraph 8.6

...The ignition has taken place, if either the flame on the sample further on at least 5 seconds after the flame is removed, or remove the sample after the flame blows up to the top edge or edges to the vertical.

2.2.1 Test results according to DIN EN 13772:

(Determination of the vertical flame spread)

Impact time of the radiator: 30s

Ignition time: 10 s


Specimen no.		1	2	3	4	5	6
Test direction	L/Q	L	L	L	Q	Q	Q
Kind of ignition	S/E	E	E	E	E	E	E
Ignition time	[s]	10	10	10	10	10	10
Total burn time	[s]	10	10	15	14	13	10
After flame time	[s]	0	0	5	4	3	0
After glow time	[s]	0	0	0	0	0	0
Reaching the 1. mark in	[s]	-	-	-	-	-	-
Reaching the 2. mark in	[s]	-	-	-	-	-	-
Reaching the 3. mark in	[s]	-	-	-	-	-	-
Flame spread v1	[mm/min]	0	0	0	0	0	0
Flame spread v2	[mm/min]	0	0	0	0	0	0
Flame spread t v3	[mm/min]	0	0	0	0	0	0
Separating of sample parts*		-	-	-	-	-	-
Ignition of the filter paper*		-	-	-	-	-	-
Destroyed area length	[mm]	150	160	170	190	140	160
Destroyed area width	[mm]	90	100	90	100	90	90

If not the case, - L = length Q = width S = surface E =edge

Remarks: No difference of the burning behaviour of front and backside

2.2.2 Appearance of the specimen after the tests

Specimen after the test according to EN 13772 length and cross to direction of production



3. Classification:

The in chapter 1 described material fulfils the requirements of the class 1 according to DIN EN 13773.

Classification DIN EN 13773				
Determination of ignition time according to EN 1101 (ISO 6940)				
ignition		No ignition		
Determination of vertical flame spread according to DIN EN 1102		Determination of vertical flame spread according to DIN EN 13772		
class 5 3. marking thread broken or burning falling sample parts	class 4 3 marking thread didn't break any falling burning sample	class 3 3. marking thread broken or burning falling sample parts	class 2 3. marking thread didn't break any falling burning sample parts	class 1 1. marking thread didn't break, no falling burning sample parts

Besonderer Hinweis

The fire test result is only valid for the in chapter 1 described material.

In the composition with other materials (for example coatings, deposits) the burning behaviour could be influenced unfavourable so that the above classification is not any longer valid.

The burning behaviour in composition with other materials has to be tested separately.

Frankfurt, 24th October 2014



P. Scheinkönig
Tester in Charge



Dipl.-Ing. T. Zachäus
Laboratory Supervisor

The results of the tests relate only to the behaviour of the test specimen which is designated in chapter one.
Test reports are only allowed to be published or reproduced, not changed in form and tenor without permission of the Exova Warringtonfire, Frankfurt.

The abridged account of a test report is only allowed with the agreement of the Exova Warringtonfire, Frankfurt.

This test report is a translation of the German version 2014-2041 (issued 24.10.2014). In case of doubt only the German version is valid.

The report contains 7 pages.