

FLAMMABILITY TEST CERTIFICATE - 66958

COMPANY DETAILS: BANCROFT SOFT FURNISHINGS
6 RUSSELL COURT, WOOL GATE, BINGLEY, BD16 1PE

CONTACT NAME(S): JESS WARD
TEL: 01274 518888
EMAIL: jessica@bancroft-linings.com

DATE RECEIVED: 23/04/2018
DATE TESTED: 25/04/2018
DATE ISSUED: 26/04/2018
PO NUMBER: BSF 177

SAMPLE DESCRIPTION: 7066 STARDUST FR DIMOUT
COLOUR: BEIGE
QUALITY/BATCH REF: NOT STATED
COMPOSITION: 100% POLYESTER
SAMPLE END USE: DRAPERY
MANUFACTURER: NOT STATED
SUPPLIER/BUYER: NOT STATED

PERFORMANCE REQUIRMENT:

BS 5867-2: 2008 Type B – Flammability requirements specification – Fabrics for curtains, drapes and window blinds.

TEST METHOD:

BS EN ISO 15025: 2002 Procedure A (Surface Ignition) – Protective clothing – Protection against heat and flame.
Methods of test for limited flame spread.

PRE-TREATMENT:- Disposable products:

One set of six specimens had been subjected to 12 wash cycles in accordance with BS EN ISO 15028: 2002 Reduced then line dried.

CONDITIONING:

The sample was conditioned for at least 24 hrs in a specified atmosphere at $20 \pm 2^{\circ}\text{C}$ and $65 \pm 5\%$ r h.

Authorised By:



Zeb Alam
Operations Director

Mark Jones
Quality Manager

Karen Brooks
Managing Director

FLAMMABILITY TEST CERTIFICATE - 66958

TEST RESULTS:

BEFORE CLEANISNG:

Test Criteria	1	2	3	4	5	6
Specimen Direction:	↑	↓	↑	←	→	←
Application Time:	15	15	15	15	15	15
Hole formed: (Y/N)	Y	Y	Y	Y	Y	Y
Hole reached the edge: (Y/N)	N	N	N	N	N	N
Flame reached the edge: (Y/N)	N	N	N	N	N	N
Flaming Debris: (Y/N)	N	N	N	N	N	N
Damage Length: (mm)	30	30	31	32	33	30
Damage width: (mm)	20	20	18	21	21	21
Test Result	PASS	PASS	PASS	PASS	PASS	PASS

AFTER CLEANISNG:

Test Criteria	1	2	3	4	5	6
Specimen Direction:	↑	↓	↑	←	→	←
Application Time:	15	15	15	15	15	15
Hole formed: (Y/N)	Y	Y	Y	Y	Y	Y
Hole reached the edge: (Y/N)	N	N	N	N	N	N
Flame reached the edge: (Y/N)	N	N	N	N	N	N
Flaming Debris: (Y/N)	N	N	N	N	N	N
Damage Length: (mm)	30	31	30	32	32	28
Damage width: (mm)	20	19	21	20	22	21
Test Result	PASS	PASS	PASS	PASS	PASS	PASS

PASS/FAIL CRITERIA:

No Part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge of the sample. If any part of any hole or any part of the lowest boundary of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing of one specimen, a further six specimens must be tested and comply with the above requirements, the fabric shall be deemed to conform to the requirements of type B of BS 5867-2

CONCLUSION:

The sample supplied **meets** the type B performance requirement of BS 5867-2: 2008 when tested in accordance with BS EN ISO 15025: 2002 Procedure A (Surface Ignition) before and after cleansing.

END OF REPORT