

## FLAMMABILITY TEST CERTIFICATE - 77695

**COMPANY DETAILS:** BANCROFT SOFT FURNISHINGS  
6 RUSSELL COURT, WOOL GATE, BINGLEY, BD16 1PE

**CONTACT NAME(S):** REBECCA PETERSON  
**TEL:** 01274 518888  
**EMAIL:** [rebecca.peterson@bancroft-linings.com](mailto:rebecca.peterson@bancroft-linings.com)

**DATE RECEIVED:** 24/09/2019  
**DATE TESTED:** 01/10/2019  
**DATE ISSUED:** 01/10/2019  
**PO NUMBER:** BSF 236

**SAMPLE DESCRIPTION:** DAZZLE FR DRAPERY FABRIC  
**COLOUR:** JASMINE  
**QUALITY/BATCH REF:** P10666  
**COMPOSITION:** 100% POLYESTER  
**SAMPLE END USE:** DRAPERY  
**MANUFACTURER:** NOT STATED  
**SUPPLIER/BUYER:** NOT STATED

### PERFORMANCE REQUIRMENT:

BS 5867-2: 2008 Type B – Flammability requirements specification – Fabrics for curtains, drapes and window blinds.

### TEST METHOD:

BS EN ISO 15025: 2002 Procedure A (Surface Ignition) – Protective clothing – Protection against heat and flame.  
Methods of test for limited flame spread.

### PRE-TREATMENT:-

One set of six specimens had been subjected to 5 wash cycles in accordance with BS EN ISO 15028: 2002 Reduced then line dried.

### CONDITIONING:

The sample was conditioned for at least 24 hrs in a specified atmosphere at  $20 \pm 2^{\circ}\text{C}$  and  $65 \pm 5\%$  r h.

Authorised By:



Zeb Alam  
Operations Director

Mark Jones  
Quality Manager

Karen Brooks  
Managing Director

## FLAMMABILITY TEST CERTIFICATE - 77695

### TEST RESULTS:

#### BEFORE CLEANISNG:

Test Criteria	1	2	3	4	5	6
Specimen Direction:	↑	↓	↑	←	→	←
Application Time:	15	15	15	15	15	15
Hole formed: (Y/N)	YES	YES	YES	YES	YES	YES
Hole reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flame reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flaming Debris: (Y/N)	NO	NO	NO	NO	NO	NO
Damage Length: (mm)	72	59	64	73	60	54
Damage width: (mm)	21	24	22	26	22	25
<b>Test Result</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>

#### AFTER CLEANISNG:

Test Criteria	1	2	3	4	5	6
Specimen Direction:	↑	↓	↑	←	→	←
Application Time:	15	15	15	15	15	15
Hole formed: (Y/N)	YES	YES	YES	YES	YES	YES
Hole reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flame reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flaming Debris: (Y/N)	NO	NO	NO	NO	NO	NO
Damage Length: (mm)	61	52	50	50	53	62
Damage width: (mm)	18	20	3	24	23	23
<b>Test Result</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>

#### PASS/FAIL CRITERIA:

No Part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge of the sample. If any part of any hole or any part of the lowest boundary of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing of one specimen, a further six specimens must be tested and comply with the above requirements, the fabric shall be deemed to conform to the requirements of type B of BS 5867-2

#### CONCLUSION:

The sample supplied **meets** the type B performance requirement of BS 5867-2: 2008 when tested in accordance with BS EN ISO 15025: 2002 Procedure A (Surface Ignition) before and after cleansing.

END OF REPORT