

Test Certificate 73729 - 1

Report Details

Report Number 73729 - 1 Date Submitted 14-Mar-19

Service Requested BS 5867-2: 2008 - Type C Date Issued 20-Mar-19

Customer Details

Company Name BANCROFT SOFT FURNISHINGS

Customer Contact Rebecca Peterson Company Address 6 RUSSELL COURT, WOOL GATE

Customer Ref/PO BSF 203 COTTINGLEY BUSINESS PARK

WEST YORKSHIRE

BD16 1PE

Sample Details As supplied by the customer

Sample Description TATTON FR DRAPERY FABRIC

Fibre Composition 100% POLYESTER

Quality/Batch Ref P11425

Colour CREAM

Sample End Use DRAPERY

Model Ref Manufacturer

Supplier / Buyer

Performance Requirement:

BS 5867-2: 2008 Type C – Flammability requirements specification – Fabrics for curtains, drapes and window blinds.

Test Method:

BS EN ISO 15025: 2002 Procedure A (Surface Ignition) – Protective clothing – Protection against heat and flame. Methods of test for limited flame spread.

Pre-Treatment:

Prior to testing, one set of specimens had been subjected to 50 standard wash cycles in accordance with BS EN ISO 15028 (Standard) and then line dried in ambient atmospheric conditions.

Conditioning:

The sample was conditioned for at least 24 hrs in a specified atmosphere at $20 \pm 2^{\circ}$ C and $65 \pm 5\%$ r h.

Pass / Fail Criteria:

No Part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge of the sample. If any part of any hole or any part of the lowest boundary of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing from any specimen, or if the mean after flame or afterglow times exceed 2.5 seconds the fabrics shall be deemed not to comply with the requirements for type "C" of BS 5867-2

Please note: The test results issued on this certificate refer only to the item tested and therefore does not relate to the lot or batch of the product / sample. This test certificate shall not be duplicated.





Test Certificate 73729 - 1

Test Results

Test 1 - Before Wash	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16
Surface Tested:	Face		Back		Face		Back		Face		Back		Face		Back	
Specimen Direction:	1	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow
Application Time:	5 Seconds		5 Seconds		15 Seconds		15 Seconds		20 Seconds		20 Seconds		30 Seconds		30 Seconds	
Flaming Ceased:	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0
Afterglow Ceased:	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0
Hole Formed:	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Hole Reached the Edge:	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No
Flame Reached the Edge:	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No
Flaming Debris:	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No
Damage Length [mm]:	43	40	44	41	63	61	58	53	60	60	58	53	60	55	62	55
Damge Width [mm]:	20	20	21	20	22	24	22	25	22	23	22	25	26	23	25	20
Average After Flame < 2.5S		0.0														
Average After Glow < 2.5S		0.0														

Please note: The test results issued on this certificate refer only to the item tested and therefore does not relate to the lot or batch of the product / sample. This test certificate shall not be duplicated.





Test Certificate 73729 - 1

Test 2 - After Wash	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16
Surface Tested:	Face		Back		Face		Back		Face		Back		Face		Back	
Specimen Direction:	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow	↑	\rightarrow
Application Time:	5 Seconds		5 Seconds		15 Seconds		15 Seconds		20 Seconds		20 Seconds		30 Seconds		30 Seconds	
Flaming Ceased:	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0
Afterglow Ceased:	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0
Hole Formed:	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Hole Reached the Edge:	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No
Flame Reached the Edge:	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No
Flaming Debris:	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No	No
Damage Length [mm]:	45	39	42	41	49	53	52	55	67	60	62	58	61	63	60	63
Damge Width [mm]:	23	20	18	20	22	22	20	20	23	22	22	22	23	23	20	21
Average After Flame < 2.5S		0.0	l		1		l		I				l		l	
Average After Glow < 2.5S		0.0														

Overall Result: PASS

The sample supplied meets the type C performance requirement of BS 5867-2: 2008 when tested in accordance with BS EN ISO 15025: 2002 Procedure A (Surface Ignition) before and after cleansing.

Authorised Signature:



Quality Manager

