

TECHNISCHE DATEN / CARACTERISTIQUES TECHNIQUES / TECHNICAL PROPERTIES

	decovin® pavone	decovin® stingray	decovin® galuchat	decovin® boa	decovin® alligator	decovin® ostra	decovin® ostra	microweb® lano FR	digitalprint
Zusammensetzung composition	Gesamt / totale / total 60 % PVC, 40 % PES 10 % PU	60 % PVC, 30 % PES, 10 % PU	74 % PVC, 25 % CO, 1 % PU	72 % PVC, 27 % CO, 1 % PU	79 % PVC, 17 % CO, 4 % PU	83 % PVC, 16 % CO, 1 % PU	72 % PVC, 27 % CO, 1 % PU	84 % PES, 16 % PU	
Oberfläche / surface Träger / support	100 % PVC 100 % PES	95 % PVC, 5 % PU 100 % CO	100 % PVC 100 % CO	100 % PVC 100 % CO	100 % PVC 100 % CO	99 % PVC, 1 % PU 100 % PES	99 % PVC, 1 % PU 100 % CO	100 % PES PU-Membrane	
Breite / largeur / width	ca. / env. / approx. 137 cm	137 cm	150 cm	150 cm	140 cm	150 cm	150 cm	145 cm	
Rollen / rouleaux / rolls	ca. / env. / approx. 27.4 m	27.4 m	30 m	30 m	30 m	30 m	30 m	50 m	
Gewichtspoids / weight	ca. / env. / approx. 578 g/m²	790 g/m²	780 g/m²	740 g/m²	650 g/m²	650 g/m²	740 g/m²	440 g/m²	
Gesamtdicke épaisseur totale total thickness	ca. / env. / approx. 1.0 mm	1.2 mm	1.8 mm	1.6 mm	1.1 mm	1.8 mm	1.7 mm	1.0 mm	
Einsatzbereich domaines d'utilisations field of application									
Rapport raccord repeat	ca. / env. / approx. –	25.4 x 27.94 cm	13 x 13 cm	–	21.1 x 19.3 cm	–	–	Design Dragon: 13.5 x 13.5 cm Design Salamander: 22.7 x 21.7 cm Design Snake: 21 x 30 cm	
Höchstzugkraft résist. à la traction	Länge / longueur / length 95 N Breite / largeur / width 60 N	180 N 180 N	250 N 200 N	350 N 250 N	300 N 230 N	200 N 200 N	300 N 200 N	300 N 200 N	
resist. to tensile strength	ISO 1421:1998								
Weiterreiss- festigkeit résistance déchirement	Länge / longueur / length 9 N Breite / largeur / width 12 N	20 N 15 N	25 N 25 N	25 N 25 N	40 N 25 N	40 N 30 N	25 N 25 N	25 N 30 N	
laceration resistance	ISO 4674-1								
Lichtechtheit résist. à la lumière light fastness	ISO 105 / B02 > 5 (XENO)	> 5	> 5	> 5	> 5	> 5	> 5	> 4	
Abrieb Martindale abrasion Martindale Martindale	Touren / tours > 50'000 EN ISO 12947-2	> 30'000	> 30'000	> 50'000	> 50'000	> 30'000	> 30'000	> 15'000	
Reibechtheit résist. de frottement resistance to rubbing	trocken / sec / dry > 4-5 nass / humide / wet > 4-5 ISO 105 - X12 (grey)	> 4-5 > 4-5	> 4-5 > 4-5	> 4-5 > 4-5	> 4 > 4	> 4-5 > 4-5	> 4-5 > 4-5	> 4 > 3	
Brandklassifizierung résistance au feu classification flame retardant	CH: SN 198898 GB: BS 5852 EU: EN 1021 IMO 2010 FTP Teil 8	Part 0 + 1 Teil 1 + 2	Part 0 + 1 Teil 1 + 2	5.2 Part 0 + 1 Teil 1 + 2 IMO A652	5.3 Part 0 + 1 / Crib 5 Teil 1 + 2 IMO A652	Teil 1	5.2 Part 0 + 1 / Crib 5 Teil 1 + 2	5.2 O + 1 / Crib 5 Teil 1 + 2 IMO A652	
Alle Daten sind Mittelwerte. Änderungen vorbehalten. Toutes les données sont des valeurs moyennes. Sous réserve de modifications. All the above data represents average values. Subject to changes.									